

NOVALLOY B series

PBT/ABS resin

Technical Information

TI-05415

Properties

B5723M

Glass fiber-reinforced flame-retardant PBT/ABS resin (GF15%)

Heat resistance

| Properties | Test methods | Test conditions | Units | |
|-----------------------------------|--------------|-----------------|-------|-----------|
| Mold shrinkage | Our standard | - | % | 0.4-0.6 |
| Tensile strength | ISO 527 | - | MPa | 85 |
| Flexural strength | ISO 178 | - | MPa | 120 |
| Flexural modulus | ISO 178 | - | MPa | 5300 |
| Notched Charpy impact strength | ISO 179/1eA | 23 deg C | kJ/m2 | 6 |
| Deflection temperature under load | ISO 75 | 1.80MPa | deg C | 170 |
| Deflection temperature under load | ISO 75 | 0.45MPa | deg C | 195 |
| Flammability | UL94 | - | - | V-0/1.5mm |
| Density | ISO 1183 | - | g/cm3 | 1.43 |

Note

- Test methods such as ISO standards are fully or almost compliant with the standards.
- Values are typical, not quality assured.
- UL recognition File No. is E47773.
- The colorant formulations are restricted for each UL certified color. Please contact us for more information.

Typical settings for processing

| Preliminary drying | Barrel temperature(deg C) | | | | Screw rotation (rpm) | Back pressure (MPa) | Mold temperature (deg C) |
|-----------------------|---------------------------|---------|---------|---------|----------------------|---------------------|--------------------------|
| | Nozzle | Front | Middle | Back | | | |
| 3-5hrs 80-120deg C | 230-250 | 240-250 | 220-240 | 190-230 | 50-90 | 5-20 | 60-80 |

Novacel Co., Ltd.

2024/07/01-0