

NOVALLOY S series

PC/ABS resin

Technical Information

TI-05404

Properties

S4100V

Flame-retardant PC/ABS resin
Standard

Properties	Test methods	Test conditions	Units	
Mold shrinkage	Our standard	-	%	0.4-0.6
Tensile strength	ISO 527	-	MPa	50
Flexural strength	ISO 178	-	MPa	79
Flexural modulus	ISO 178	-	MPa	2200
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m ²	14
Notched Izod impact strength	ASTM D256	23 deg C/6.4mm	J/m	140
Deflection temperature under load	ISO 75	1.80MPa	deg C	99
Deflection temperature under load	ASTM D648	1.82MPa/6.4mm	deg C	103
Coefficient of linear thermal expansion	ISO 11359	MD	X1E-5/deg C	8
Coefficient of linear thermal expansion	ISO 11359	TD	X1E-5/deg C	-
Flammability	UL94	-	-	V-0/0.8mm 5VA/2.0mm
Hot wire ignition	UL746A	1.5mm	sec(PLC)	33(2)
High ampere arc ignition	UL746A	1.5mm	arcs(PLC)	150(0)
Water absorption	ISO 62	-	%	0.3
Density	ISO 1183	-	g/cm ³	1.23

Note

- Test methods such as ISO standards are fully or almost compliant with the standards.
- Values are typical, not quality assured.
- UL recognition File No. is E47773.
- The colorant formulations are restricted for each UL certified color. Please contact us for more information.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
4-5hrs 90-110deg C	220-250	230-250	220-240	200-230	50-100	5-20	60-80

Novacel Co., Ltd.

2024/07/01-0